

Product: CeRam-Kote SPG22
Chemical resistance testing

Test Procedure: Conducted per ASTM D543
Immersion temperature = 77°F (25°C)

Solvent Resistance

Reagent	Recommendation
Xylene	Yes
Toluene	Yes
Butyl Cellosolve	Yes
Trichloroethane	Yes
Ethylene Glycol	No
Methyl Ethyl Ketone	Yes
Ethanol	No
Methanol	No

Hydrocarbon and Water Resistance

Reagent	Recommendation
Skydrol	Yes
Diesel Fuel	Yes
Gasoline (93 Octane)	Yes
Hydraulic Fluid	Yes
Motor Oil	Yes
Propane	Yes
Sweet crude	Yes
Deionized Water	Yes

Acid / Base Resistance

Reagent	Recommendation
10% Acetic Acid	Yes
5% Acetic Acid	Yes
10% Lactic Acid	Yes
70% Sulfuric Acid	Yes
98% Sulfuric Acid	Yes
50% NaOH	Yes
10% Sodium Hypochlorite	Yes